

TRILITE® CLR-B3

Chelating Resin for Boron Removal

Rev.1 July 2018

TRILITE® CLR-B3 is a superior grade chelating resin with high selectivity to boron. The resin has high selective that it could remove boron from any salt background, it operates nearly like a universal resin for boron without interfered by other ions or boron concentration in solutions.

- 1) Boron removal from drinking water
- 2) Boron removal for water used in irrigation
- 3) For boron removal from magnesium brine
- 4) Waste water containing boron

Physical and Chemical Properties

Physical Form	Beige opaque beads	Matrix	Styrene-DVB, Macroporous
Functional Group	N-Methylglucamine	Ionic Form	Free Base
Total Capacity(eq/ℓ)	0.6eq/ℓ as boron ↑	Moisture Retention(%)	48~54
Shipping Density(g/ℓ)	660 ~750	Particle Density	1.10
Uniformity Coefficient	1.6 ↓	Particle Size(mm)	0.30~1.25
Whole Beads(%)	95 ↑	Swelling Rate(%) (FB → Cl ⁻)	10

Recommended Operating Conditions

Operating Temp(°C)	80 ↓	Operating PH	2~7
Bed Depth(mm)	800	Service Flow Rate(BV/h)	5~20
Eluting			
Eluate	HCl, H ₂ SO ₄	Concentration(%)	2~3.5
Level(g/ℓ)	55~100	Flow Rate(m/h)	50~70
Regeneration			
Regenerant	NaOH	Concentration(%)	2~4
Level(g/ℓ)	20~40	Flow Rate(BV/hr)	1~3
Rinse Requirement(BV)	10~15 (Softened Water)		

Samyang's TRILITE Ion exchange resins are produced based on the ISO 9001, ISO 14001 certification.

Samyang Corporation, 31 Jong-ro 33-gil, Jongno-gu, Seoul, Korea Tel: (02)740-7732~7, Fax: (02)740-7140



<http://samyangtrilite.com>