

TRILITE® MC-08H

Uniform Particle Size Strong Acid Cation Exchange Resin

Rev.2 Nov 2018

TRILITE® MC-08H Strong Acid Cation Exchange Resin is a Gel Type Uniform Particle Size resin. Because of its excellent ion removal capacity, high purity water can be produced economically. TRILITE® MC-08H is a standard cross-linkage product and it has outstanding mechanical and chemical stability, leading to low crush rate even after long-term use. TRILITE® MC-08H can be supplied by H⁺ form but Na⁺ form can be available depending on application and user's request.

Physical and Chemical Properties

Physical Form	Khaki translucent spherical beads	Matrix	Styrene-DVB, Gel
Functional Group	Sulfonic acid	Ionic Form	H ⁺
Total Capacity(eq/ℓ)	1.80 ↑	Moisture Retention(%)	50~56
Shipping Density(g/ℓ)	800	Particle Density	1.20
Uniformity Coefficient	1.1 ↓	Particle Size(μm)	620±50
Whole Beads(%)	95 ↑	Swelling(Na ⁺ →H ⁺ , %)	9

Recommended Operating Conditions

Operating Temp(°C)	120	pH Range	0~14
Bed Depth(mm)	800	Service Flow Rate(m/h)	5~60
Regeneration			
Regenerant	HCl, H ₂ SO ₄	Concentration(%)	HCl(1~8), H ₂ SO ₄ (1~4)
Level(g/ℓ)	30~150	Flow Rate(m/h)	2~10
Rinse Requirement(BV)	2~6		

Applications

TRILITE® MC-08H is widely used for softening, demineralization, and other special processes like catalyst reaction.

Hydraulic Characteristics

Figure 1 and 2 show the backwash expansion of TRILITE® MC-08 as a function of flow rate and temperature.




Figure 1. TRILITE® MC-08 Na⁺ Type




Figure 2. TRILITE® MC-08 H⁺ Type

Figure 3 and 4 show the pressure drop of TRILITE® MC-08 as a function of flow rate and water temperature.




Figure 3. TRILITE® MC-08 Na⁺ Type




Figure 4. TRILITE® MC-08 H⁺ Type

All information contained in brochure is not absolute rather than relative one, created under the controlled environment by Samyang Corporation. Therefore, Samyang Corporation has no legal responsibility with respect to any and all information provided in brochure.

Samyang's TRILITE Ion exchange resins are produced based on the ISO 9001, ISO 14001 certification.
 Samyang Corporation, 31 Jong-ro 33-gil, Jongno-gu, Seoul, Korea Tel: (02)740-7732~7, Fax: (02)740-7140



<http://samyangtrilite.com>